



MIROKEY VY 6615 Etch Primer

MIROKEY VY 6615 is a high performance, zinc phosphate etch primer specifically designed for direct application over mild steel, zinc-anneal, chrome, brass, lead and lead alloys, stainless steel, aluminium and galvanised iron.

Product Advantages

- Excellent adhesion to a variety of cleaned metal surfaces
- Single pack, easy to use
- Contains zinc phosphate, proven corrosion resistance
- Fast drying

Typical Applications

Metal fabrication, box trailers, caravans, safes, plant & machinery, farming equipment, earth moving equipment, skip bins and automotive.

Product Properties

Build:	Good
Sandability:	No sanding required
Vertical Hold Up:	Excellent
Solvent Resistance:	Dependent upon topcoat
Water Resistance:	Very good
Levelling & Flow:	Very good
Sink Back:	Minimal

Typical Properties

Colour:	White, Grey & limited colour range
---------	------------------------------------

Coverage: 7-10 m² per litre at 150 micron wet film build. This is dependent on the application equipment / gun set up and the article being coated.

Thinning: Thin 5 to 15% with MIROSOL 1234 or 1286 Ultra-Fast Thinners or 1294 Medium Thinner.

Application Viscosity: 18-24 seconds BS4 Flow Cup at 25°C.

Wet Film Thickness (WFT): 100-150 microns per coat.

Application Methods:

Suction Gun:	Use 1.5 to 2mm (59-79 thou) orifice with 350-400kpa (50-55 psi).
Pressure Pot:	Use 1.5 to 2mm (59-79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.
Airless Spray:	Use 0.23 to 0.33mm (9-13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).
Air Mix Guns:	Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).
Brush / Roller:	Apply even coats to the recommended film build.

Drying: Dust Free: 5-7 minutes
Touch Dry: 10-15 minutes
Topcoat: 3-4 hours
Block Stacking: 24 hours

Temperatures below 16°C will retard the curing reaction of the product. Drying time is also affected by wet film thickness, the higher the WFT the slower the rate of reaction and the longer the dry time.

Surface Preparation: Remove contaminants by washing the surface with MIROSOL 1231 Wax & Grease Remover. Ensure all corrosive products, soluble salts, rust, millscale, loose or flaky paint is removed prior to coating. Linishing or abrasive blast cleaning may be required. At the time of application, the surface should have a surface temperature of between 18 to 25°C to reduce the risk of loss of adhesion due to condensation.

Metal Surface Preparation: Remove contaminants by washing the surface with MIROSOL 1231 Wax & Grease Remover. Ensure all corrosive products, soluble salts, mill scale, loose or flaky paint is removed prior to coating. Linishing or abrasive blast cleaning may be required. At the time of the application, the surface should have a surface temperature of between 18 to 25°C to reduce the risk of loss of adhesion due to condensation.

Aluminium, Galvanised Steel & Zinalume: Thoroughly clean the surface with MIROSOL 1231 Wax & Grease Remover. Apply one light coat of MIROKEY VY 6615 to provide adhesion for the following coats of MIROLON 6930 Primer or one of the recommended Mirotone topcoats. Apply MIROLON 6930 over MIROKEY VY 6615 when a higher build sanding primer is required. Allow to dry & apply the recommended Mirotone metal topcoat.

Recommended Topcoats:

Exterior: MIROTHANE PU 5610 Two Pack Acrylic Modified Polyurethane
MIROLON AK 6980 High Build Gloss Topcoat
Alkyd enamel topcoats designed for exterior exposure
Suitable exterior grade two pack polyurethane coating

Interior: MIROBILD AC 3770 Pigmented Topcoat
MIROTHANE PU 5605 or 5650 Polyurethane Pigmented Topcoats

Note: Do not apply MIROLON AK 6970 Rapid Dry Topcoat over MIROKEY VY 6615 Etch Primer

Application Equipment Clean Up: Clean all equipment using MIROSOL 1234 or 1286 Thinner

Shelf Life: 24 months
Packaging: 4 & 20 litres

Health & Safety

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

Mirotone Pty Ltd Australia (Head Office)
ABN 40 000 041 136
21 Marigold Street,
Revesby NSW 2212 Australia
P +61 2 9795 3700 F +61 2 9771 3601
sales@mirotone.com.au

Mirotone (NZ) Ltd New Zealand (Head Office)
32 Cryers Road,
Auckland, 1730, New Zealand
P +64 9 272 2730 F +64 9 272 2733
information@mirotone.co.nz

Mirotone (Thailand) Co., Ltd
83 Moo 4, Poochaosamingprai Rd,
Samrong Klang, Prapradaeng,
Samutprakam, 10130, Thailand
P +66 2 754 4451 F +66 2 754 4450

www.mirotone.com