



Product Easy Find Guide



MIROTONE

mirotone.com

MIROLAC NC Nitrocellulose Lacquers - Pigmented

Typical Application	Product No	Description	Pack Sizes	m ² /Lt	Shelf Life (Mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow	
Children's toys & furniture Domestic furniture e.g. bookcases, chairs, bedroom furniture, wardrobes	NC 3121	Universal NC White Undercoat	20 L	6 m ²	24	MIROBILD NC 3150, MIROBILD AC 3770, MIROTHANE PU 5650, 5605	Spray Curtain Coater Electrostatic spray	25-40% V – 18-20 sec Sand – 30 min	1222	1294	1242	
	NC 3125	Universal NC White Undercoat (Fast drying, *phthalate free)	4, 20 L	6 m ²	24		Spray Curtain Coater	25-40% V – 20 - 30 sec Sand – 25 min				
	NC 3130	NC White Undercoat	4, 20 L	6 m ²	24	MIROLAC NC 3150	Spray	25-40% V – 45 - 55 sec Sand – 30-60 min				1297 (hot conditions)
	NC 3150	NC Pigmented Topcoat (10, 30, 60, Full Gloss) *phthalate free	4, 20 L	8 m ²	24	MIRLAC NC 3121, 3125, 3130, MIROBILD AC 3720, MIROTHANE PU 5600, 5626, 5631	Spray	10 - 20% V – 50 - 55 sec Sand – 60 - 90 min				

*Phthalate free – safer for children's toys and furniture

For full product details visit www.mirotone.com for Product Data Sheets, Safety Data Sheets and Product Information Guides

MIROCAT PC Precatalysed Lacquers - Clear

Typical Application	Product No	Description	Pack Sizes	m ² /Lt	Shelf Life (Mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow
Domestic furniture e.g. bookcases, chairs, bedroom furniture, wardrobes Wall and ceiling panels	PC 3241	Ready for Use Sealer	20 L	6 m ²	24	MIROCAT PC 3210, 3220	Spray	0-5% V – 50-60 sec Sand – 2-3 hrs	1222	1294	1242 1297 (hot conditions)
	PC 3242	Sealer for Timber & MDF (Clear or Black)	4, 20 L	6 m ²	24	MIROCAT PC 3210, 3220	Spray	10 - 20% V – 30-50 sec Sand – 2-3 hrs			
	PC 3244	Rapid Dry Sealer (High Build)	20 L	6 m ²	24	MIROCAT PC 3210, 3220, MIROBILD AC 3606, 3646, 3690	Spray	15-25% V – 50-60 sec Sand –XXX min			
	PC 3210	Single Pack Clear Topcoat (30%, 60%)	20 L	6 m ²	24	MIROCAT PC 3241, 3242, 3244, MIROTHANE PU 5545	Spray	0-5% V – 40-48 sec Sand – 2-3 hrs			
	PC 3220	Single Pack Clear Topcoat (10, 30, 60, Full Gloss)	4, 20 L	6 m ²	24	MIROCAT PC 3220, 3241, 3242, 3244, MIROTHANE PU 5545	Spray	Low Gloss 0-5% Full Gloss 20-30% V – 50-60 sec Sand –2-3 hrs			

MIROBILD AC Acid Catalysed Coatings - Clear

Typical Application	Product No	Description	Pack Sizes	m ² /Lt	Shelf Life (mths)	Mirotone Sealer / Topcoat	Pack B	Application Equip	Thinning Ratio	Fast	Med	Slow
Domestic furniture e.g. dining and coffee tables, bedroom furniture, commercial furniture e.g. desks, tables, chairs, wall and ceiling panels, kitchens, bathroom vanities *Always test the substrate before application as many timbers or veneer/glue combinations can discolour when coated with acid catalysed coatings (i.e. huon pine, myrtle, Tasmanian blackwood or beech). Use a MIROTHANE PU clear coating system to reduce the risk of discolouration.	AC 3622	Clear Rapid Dry Sealer	4, 20 L	6-7 m ²	18	MIROBILD AC 3606, 3646, 3680	AC 3800 10A: 1B Universal catalyst Packs: 500ml, 2L, 4L, 20L AC 3810 10A:1B Quick dry catalyst Packs: 2L, 20L	Spray Curtain Coater	10-15% V – 25-35 sec Sand – 40-60min	1220 1222	1294	1242 1297 (hot conditions)
	AC 3606	Low yellowing, low formaldehyde topcoat (10, 30, 60, Full Gloss)	4, 20 L	6-7 m ²	18	MIROBILD AC 3622, 3606, 3628, 3241, 3242, 3244, MIROTHANE PU 5533			Up to 30% V – 40-50 sec Sand – 2 ½ hrs			
	AC 3646	Low yellowing clear topcoat (30, 60%)	20 L	6-7 m ²	18	MIROBILD AC 3622, MIROCAT PC 3244, MIROTHANE PU 5533			5-15% V – 20-25 sec Sand – 40-90 min			
	AC 3690	Ultra gloss casket lacquer (Full Gloss)	20 L	6-7 m ²	18	MIROBILD AC 3622,			10-25% V – 18-25 sec Sand – 40-90 mins			

*Shelf life for MIROBILD AC 3800 and 3810 is 12 months

For full product details visit www.mirotone.com for Product Data Sheets and Product Information Guides

MIROBILD AC Acid Catalysed Coatings - Pigmented

Typical Application	Product No	Description	Pack Sizes	M ² /Lt	Shelf Life (months)	Mirotone Sealer / Topcoat	Pack B	Application Equip	Thinning Ratio	Fast	Med	Slow
Domestic furniture e.g. dining and coffee tables, bedroom furniture, commercial furniture e.g. desks, tables, chairs, wall and ceiling panels, kitchens, bathroom vanities	AC 3720	White Undercoat	20 L	6-7 m ²	18	MIROBILD AC 3770	AC 3800 10A: 1B Universal catalyst Packs: 500ml, 2L, 4L, 20L	Spray Curtain Coater	0-20% V – 40-50 sec Sand – 2-3 hrs	1220	1294	1242 1297 (hot conditions)
	AC 3770	Two Pack Pigmented Topcoat (30, 60, Full Gloss)	4, 20 L	6-7 m ²	18	MIROLAC NC 3125, MIROBILD AC 3720, MIROTHANE PU 5600, 5626, 5631, VY 6615	AC 3810 10A:1B Quick dry catalyst Packs: 2L, 20L		25-35% V – 25-35 sec Sand – 1 hr			

*Shelf life for MIROBILD AC 3800 and 3810 is 12 months

For full product details visit www.mirotone.com for Product Data Sheets and Product Information Guides

MIROTHANE PU Polyurethane Coatings - Clear												
Typical Application	Product No	Description	Pack Sizes	M ² /L	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Part B	Thinning Ratio	Fast	Med	Slow
Isolator for oily timbers and difficult substrates	PU 5500	1K or 2K Isolator Coat – No sanding Barrier Coat	4, 20 L	10 m ²	24	All	Spray	PU 5789 10A:1B	1K – 20-30% 2K – 12-25% V - 18-23 sec Recoat – 1K – 1 hr 2K – 2 hrs	1217	1263	1266
Domestic furniture e.g. dining and coffee tables, bedroom furniture, commercial furniture e.g. desks, tables, chairs, wall and ceiling panels, kitchens, bathroom vanities	PU 5533	Furniture Grade Polyurethane Sealer	20 L	8 m ²	12	MIROCAT 3220, MIROTHANE PU 5588, 5555	Spray	PU 5747 4A:1B	10-20% V – 20 sec Sand – 1 hr	1217	1263	1266
	PU 5588	Furniture Grade Polyurethane Topcoat (30%)	20 L	6-7 m ²	12	MIROBILD PU 5533, 5545, MIROCAT PC 3241, 3242, 3244, MIROTHANE PU 5588	Spray		PU5715, 5728, 5735, 5757 10A:1B			
All of the above plus bathroom vanity and bar tops	PU 5545	Marine Grade Clear Polyurethane Sealer	4, 20 L	6-7 m ²	12	MIROTHANE PU 5555, 5577, MIROCAT PC 3220	Spray	PU 5747 2A: 1B PU 5715 5728, 5735, 5757, 4A:1B	10-20% V – 18 sec Sand – 1-2 hrs	1217	1263	1266 1218
	PU 5555	Marine Grade Clear Polyurethane Topcoat (30, 60, Full Gloss)	4, 20 L	6 m ²	12	MIROTHANE PU 5533, 5545	Spray	30 & 60% PU 5747 1A:1B PU 5728, 5735, 5757 2A:1B FG PU 5780 1A:1B PU 5715, 5735, 5757, 5776, 5784, 5789 2A:1B	Low gloss 30-50% FG 10-20% Refer to datasheet V – 16-18 sec Sand – 1 – 2 hrs			

MIROTHANE PU Polyurethane Coatings - Clear

Typical Application	Product No	Description	Pack Sizes	M ² /L	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Part B	Thinning Ratio	Fast	Med	Slow
Interior use, ideal for reconstituted, dyed and natural wood veneers Semi exterior e.g. covered entry doors and internal faces of opening windows	PU 5577	Sunshield Clear Polyurethane Topcoat (10, 30, Full Gloss) Contains UV absorbers	4, 20 L	6-7 m ²	12	MIROTHANE PU 5500, 5577	Spray	10 & 30% PU 5735 4A:1B FG PU 5757 4A:1B	10, 30 Thin 40-60% FG thin up to 15%	1217	1263	1266 1260

MIROTHANE PU Polyurethane Coatings - Pigmented

Typical Application	Product No	Description	Pack Sizes	M ² /Lt	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Part B	Thinning Ratio	Fast	Med	Slow
Commercial furniture e.g. desks, tables, chairs, wall and ceiling panels, kitchens, bathroom vanities	PU 5600	Two Pack Pigmented Polyurethane White Undercoat	4, 16 L	6-7 m ²	12	MIROBILD AC 3770, MIROTHANE PU 5605, 5650	Spray Curtain Coater	PU 5747 2A:1B PU 5715, 5728, 5735, 5757 4A:1B	0-50% V – 20-30 sec Sand – 3 hrs	1217	1263	1266 1218
	PU 5626	Two Pack Premium Grade, High Solids, Low Viscosity Polyurethane Undercoat (White, Black, Tinted)	5Kg (3.4L) 25kg (17L)	6-7 m ²	12	MIROTHANE PU 5605, 5650		PU 5747 3A:1B PU 5715, 5728, 5735 5A:1B	0-20% V – 25-30 sec Sand – 6 hrs			
	PU 5631	Two Pack High Solids, Low Viscosity Polyurethane Undercoat (White & Tinted slight sheen)	5Kg (3.4L) 25kg (17L)	6-7 m ²	12	MIROTHANE PU 5605, 5650		PU 5747 2A:1B PU 5715, 5728, 5735 4A:1B	0-40% V – 20-30 sec Sand – 5-7 hrs			

MIROTHANE PU Polyurethane Coatings - Pigmented

Typical Application	Product No	Description	Pack Sizes	M ² /Lt	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Part B	Thinning Ratio	Fast	Med	Slow
Commercial furniture e.g. desks, tables, chairs, wall and ceiling panels, kitchens, bathroom vanities	PU 5605	Premium High Gloss Two Pack Polyurethane Topcoat (White & Tinted Full Gloss)	1-16 L	10 m ²	12	MIROPOL PE 5110, 5111, 5130, MIROTHANE PU 5600, 5626, 5631	Spray	PU 5747 or 5780 1A:1B PU 5757, 5776, 5784, 5789 2A:1B Refer to DS for flattening base info	20-40% V – 17-22 sec Sand – 16 hrs	1217	1263	1266 1218 1281 Matt Promoter may be used with 5650/30 to achieve a matt finish
	PU 5650	Two Pack Fast Cure Polyurethane Topcoat (30, 60, Full Gloss)	1-16 L	8 m ²	12	MIROLAC NC 3125, MIROPOL PE 5110, 5111, 5130, MIROTHANE PU 5600, 5626, 5631	Spray	Satin & Semi Gloss PU 5747 1A:1B Full Gloss PU 5780 1A:1B Refer to DS for other Part B options	Satin & Semi Gloss 40-55% Full Gloss Up to 25% V – 17-20 sec Sand – 100 mins			
	PU 5673	Two Pack Rapid Dry Polyurethane Topcoat (White & Tinted Colour 30%)	1-16 L	6-7 m ²	A 24 B 12	MIROPOL PE 5110, 5111, 5130, MIROTHANE PU 5600, 5626, 5631	Spray	PU 5747 4A:1B Standard mix or PU 5747 2A:1B (Refer to DS)	20-40% V- 20 – 25 sec Sand – 1-2 hrs			
	PU 5690	Two Pack fast cure polyurethane topcoat	1-16 L	6 m ²	A 24 B 12	MIROPOL PE 5107, 5110, 5111, 5130, MIROTHANE PU 5600, 5626, 5631	Spray	PU 5728, 5735, 5757 (2A:1B)	25-30% V- 16 – 18 sec Sand – 16 hrs			

MIROTHANE PU Polyurethane Coatings - Pigmented

Typical Application	Product No	Description	Pack Sizes	M ² /Lt	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Part B	Thinning Ratio	Fast	Med	Slow
Exterior Grade, petrochemical industry e.g. Road tankers, tank farms, exterior metal surfaces, marine environment, concrete mixer bowls, multistorey buildings & structures	PU 5610	Two Pack High Performance Acrylic Modified Polyurethane Topcoat (Full Gloss only)	4, 20L	6 m ²	18	MIROKEY 6615 for aluminium, zinc and steel where a fast recoat is required MIROTHANE PU 5600, 5626, 5631 MIRPOL PE 5110, 5111	Spray	PU 5789 4A:1B	25-40% V – 17-25 sec Sand - Overnight	-	-	1266 1218 1260

MIROTHANE PU – Metallic / Pearlescent Basecoat

Typical Application	Product No	Description	Pack Sizes	M ² /Lt	Shelf Life (mths)	Mirotone Topcoat	Pack B	Application Equip	Thinning Ratio	Fast	Med	Slow
Commercial office, furniture, desks, tables, wall and ceiling panels, kitchens, bathroom vanities	PU 5640	2K Fast Drying Two Pack Polyurethane Metallic/Pearlescent Tint Base (Medium/Coarse Metallic pigment & Fine/Coarse Pearlescent)	1 – 16 L	13 m ²	24	All Clear MIROLAC NC, MIROCAT PC, MIROBILD AC, MIROTHANE PU, MIROPOL PE, MIROTEC WB	PU 5789 10A:1B	Spray Cross Hatch	50-70% V 15 – 18 sec	1217 1224 1232	-	-

MIROPOL PE POLYESTER COATINGS

Typical Application	Product No	Description	Pack Sizes	M ² /L	Shelf Life (Mths)	Mirotone Sealer / Topcoat	Pack B	Application Equip	Thinning Ratio	Fast	Med	Slow
Commercial office, furniture, desks, tables, wall and ceiling panels, kitchens (not tops), bathroom vanities	PE 5110	High Build Easy to Sand White Polyester Undercoat for MDF & Particleboard	Part A 18L 25Kg	3 m ²	12	MIROTHANE PU 5605, 5650, 5673, 5679, 5610	100:2:1 PE 5202 Cobalt (Premix 5202-360ML) PE 5249 Peroxide	Spray	30-40% V 25 – 35 sec Sand 16 hrs	1208	1234	1224
	PE 5111	Premium, High build, White Polyester Undercoat for MDF and Particleboard	Part A 17.5L 25Kg	3 m ²	12		100:2:1 PE 5202 Cobalt (Premix 5202-350ML) PE 5249 Peroxide		30-40% V 30 sec Sand - 7 hrs			
	PE 5130	High Build White Polyester Undercoat for MDF and Particleboard	Part A 17L 25Kg	3 m ²	12		100:2:1 PE 5202 Cobalt (Premix 5202-340ML) PE 5249 Peroxide		Up to 30% V 25 – 30 sec Sand 18 hrs			

MIROTEC WATER BASED COATINGS											
Typical Application	Product	Description	Pack Sizes	M ² / L	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow
Domestic & Commercial furniture, children's toys and furniture, picture frames, musical instruments, joinery, wall panelling & antique restoration	WB 8022	Clear Single Pack Low VOC Green Star Rated Water Based Sealer (Water White)	5 & 20 L	7 m ²	24	MIROTEC WB 8060, 8052	Stainless Steel Spray, Curtin Coater, Dip or Brush	Up to 5% V 45 – 50 sec Sand – 1.5-2 hrs		Water	
	WB 8060	Clear single pack Low VOC Green Star Rated water based topcoat, low yellowing (10, 30, 60%)	20 L	7 m ²	24	MIROTEC WB 8022, 8060	Stainless Steel Spray, Curtin Coater & DIP	10 - 15% V 25 – 30 sec Sand – 1.5 – 2 hrs		Water	
		(FG MTO Min Order 200L)	200 L								
Commercial office, furniture, desks, tables, wall and ceiling panels, kitchen, doors & panels (not tops) bathroom, timber hand railings and timber shutters and blinds	WB 8052	High performance clear single pack water based topcoat (10, 30%) (60%, Full Gloss Made to order Min Order 200L)	10% -20 L 30% - 5 & 20L 200 L	8 m ²	24	MIROTEC WB 8022, 8052	Stainless Steel Equipment	Up to 10% V 55 – 65 sec Sand – 1.5 - 2 hrs		Water	

Note: Must use stainless steel equipment

For full product details visit www.mirotone.com for Product Data Sheets and Product Information Guides

MIROSTAIN WOOD STAINS											
Typical Application	Product No	Description	Pack Sizes	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio (Toning)	Fast	Med	Slow	Ultra Slow
Domestic furniture e.g. dining and coffee tables, Commercial office, furniture, desks, tables, wall and ceiling panels, kitchen, doors, panels & tops, bathroom vanities and tops	ST 2010	Medium – Fast dry ready for use (RFU) dye stain (FRS)	4, 20, 60, 205 L	60	MIROCAT PC 3241, 3242, 3244, MIROBILD AC 3622, 3628, MIROTHANE PU 5533, 5545	Spray or wiping	10%	1220	1294	1242 1260	1218
	ST 2013	Slow dry RFU dye stain (FRS)	4, 20, 60, 205 L	60		Spray, wiping, brushing or dipping					
	ST 2616	High strength RFU pigment stain (Spirit stain)	4, 20, 60, 205 L	18	MIROCAT PC 3241, 3242, 3244, MIROBILD AC 3622, 3628, MIROTHANE PU 5533, 5545	Spray, wiping or brushing	10%	1222	1231	1242	1228 1233
	WB 2101	Low VOC water based RFU dye stain	5, 20L	60	MIROCAT PC 3241, 3242, 3244, MIROBILD AC 3622, 3628, MIROTHANE PU 5533, 5545, MIROTEC WB 8022	Spray, wiping, brushing or dipping	Lighter tones reduce with MIROSTAIN WB 2101 CTB				

Colour:	Custom matched to order	
2010 Primary Colour:	#5000 Yellow	#7270 Crimson
	#5067 Orange	#8000 Blue
	#7000 Red	#9999 Black
Tint Strength:	TV - Ultra Strong Tint, TX - Strong Tint, TY - Medium Tint, TZ – Light Tint	

Metal Coatings											
Typical Application	Product No	Description	Pack Sizes	M ² / L	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow
Truck & Body builders for chassis, tray stays and bumper irons	CHASSIS Black 3590	Black primer and finish coat used to paint metal truck parts (Black Japan)	10 L		12		Brush Conventional Spray	10 % V 18 – 23 sec			1228
Metal fabrication, box trailers, caravans, safes and structural steel (mild steel, zinc-anneal, chrome, brass, lead & lead alloys, stainless steel, aluminium & galvanised steel)	VY 6615	Single pack high performance etch primer - provides protective film (Matt - white & grey)	4 & 20L	7-10 m ²	24	Exterior: MIROTHANE PU 5610 Interior: MIROBILD AC 3770, MIROTHANE PU 5605, 5650	All spray equipment	5-15 %	1234 1286	1294	
Bull bars, hand rails, light office furniture/chairs, filing cabinets, general internal metal furnishings and aluminium	VY 6640	Single pack primer for application on steel surfaces (Satin - black)	4 & 20L	7-10 m ²	24		All spray equipment	5-10%	1286		

Specialty Coatings

Typical Application	Product No	Description	Pack Sizes	M ² /L	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow
Glass splashbacks, toughened glass countertops, glass furniture and glass feature walls	MIROLOK 3508	Fast drying primer & cleaner for glass	1 & 5 L		24	MIROTHANE PU 5605, 5640, 5650/30, 5650/FG	Soft lint free cloth Plastic trigger spray back	RFU			
Plastic & melamine surfaces, acrylic, vinyl & LPM	MIROLOK 3512	Fast drying clear primer, plastic	4 & 20L	10 m ²	24		All spray equipment	RFU			
Provides a white strippable coating for galvanised metal spray booths (over metal only)	STRIPCOAT 3520 White	Single pack temporary coating Booth strip	20 L	5 m ²	12		All spray equipment	V 18 – 23 sec	1222		

SPECIALTY ADDITIVES						
Typical Application	Product No	Description	Pack Sizes	Shelf Life (mths)	Mirotone Sealer / Topcoat	Addition Rate
Interior use, ideal for reconstituted, dyed and natural wood veneers	MIROSHIELD UV 3900	MIROSHEILD 3900 UV absorber additive. Minimises colour shift of sensitive substrates when exposed to UV light	1 L	24	MIROCAT PC 3241, 3242, 3244, 3210, 3220, MIROBILD AC 3622, 3606, 3646, MIROTHANE PU 5500, 5533, 5545, 5555, 5588	Ref to data sheet
Semi exterior e.g. covered entry doors and internal faces of opening windows	WB 8910	MIROSHEILD WB 8910 UV Absorber added to MIROTEC WB coatings provides a UV filter to reduce the effects of UV light on the coating & timber below	1 L	24	MIROTEC WB 8022, 8052, 8060, AQUAPRO 8020, 8068, 8270	N50 ml/L
Texture effect	MIROTEX 3934 (Fine)	MIROTEX Universal Texture Additives	1 & 4L	24	MIROLAC NC 3150, MIROBILD NC 3770, MIROTHANE PU 5605, 5610, 5650	6:1 4:1
	MIROTEX 3937 (coarse)		4 L			
Metallic effect	MIROTALLIC 3940 (Medium)	MIROTALLIC Metallic Additives	1 & 4L	24	MIROTHANE PU 5640	Up to 10% 100ml/L
	MIROTALLIC 3944 (Coarse)		1 & 4L			
Pearl Effect	MIROPEARL 3950 (Fine)	MIROPEARL Pearlescent Additive **	1 L	24	MIROBILD AC 3606 (30, 60% MIROBILD AC 3690 (60%) MIROTHANE PU 5555 (30, 60%)	1% (10ml per 1L)
	MIROPEARL 3957 (Coarse)		1 L			
Flatting Base	PU 5711	MIROCURE UV 5711 Flatting Base Added to MIROTHANE PU 5605 to drop gloss level	1 L	12	MIROTHANE PU 5605	3:1 (semi gloss) 3:1.5 (satin)
Accelerator	PU 5795	MIROTHANE PU 5795 Accelerator Designed to improve the through curing of recommended MIROTHANE PU coating systems	1 L	12	Refer to MIROTHANE PU Data Sheets	Up to 3% (30 ml/L)

**May be pre added into MIROTHANE PU 5555 – use 5555-3A-PTB-XX or 5555-9A-PTB-XX

For full product details visit www.mirotone.com for Product Data Sheets and Product Information Guides

AFTER CARE RANGE					
Typical Application	Product No	Description	Pack Sizes	Shelf Life (mths)	Application Equip
Paint Stripper: Paint, nitrocellulose, precatylised lacquers, alkyd paints, acid catalysed and polyurethane coatings	1019	MIROSTRIP 1019 Paint Stripper designed to remove previous paint films from timber and metal surfaces	4, 20 L	24	Brush
Children's toys, furniture, trophy bases, carved ornaments & nursery furniture	1012-002	MIROWAX 1012 RFU natural wax polish and finishing cream (natural colours)	750G & 3KG can	36	Soft cloth and spray
Furniture polish, low gloss kitchen cupboards & Laminex bench tops	1012-004	SPRAYGLOW 1012 Aerosol Furniture polish (low gloss)	200 G	24	Spray , Soft cloth
Furniture	1012-005-3	SPRAYLAC 1012 precatylised clear lacquer suitable for repairing small scratches and defects in furniture (Satin & Semi Gloss)	300 G	24	Apply direct from can
	1012-005-6				

PUTTIES & WOOD FILLERS											
Typical Application	Product No	Description	Pack Sizes	M ² Per Lt	Shelf Life (mths)	Mirotone Sealer / Topcoat	Application Equip	Thinning Ratio	Fast	Med	Slow
Antique Furniture and open grain timbers & Veneers	1702	MIROFIL 1702 is a hand applied filler designed to fill open timber grains before coatings are applied	4 L		24	Mirotone coatings	Apply by hand with porous cloth e.g. hessian	15%			1228